

DOP - 14.1

DOP 14.1 - 18/03/24 - Ref 24-V2-GB - Cancels and supersedes any previous versions



TEBOFLOOR
TEBOFLOOR WEATHERSCREEN
TEBOROOF
TEBOROOF WEATHERSCREEN

1. **Identification code:** Plywood 100% Maritime Pine - EN 636-3 S
 2. **Type number:** 100% Maritime Pine for exterior conditions
 3. **Intended use:** Structural exterior
 4. **Manufacturer:**
SIB THEBAULT SAS - 20 rue de Saunière - 79190 Sauzé-Vaussais - France
THEBAULT PLYLAND SAS - 6, piste 36A JP Darrigade - 40210 Solférino - France
 5. **Authorized representative:** not applicable
 6. **System of assessment and verification of constancy of performance:** 2+
 7. **Certificate of conformity of the factory production control issued by:** FCBA (0380)
 8. **European technical assessment:** not applicable
 9. **Declared performances:** harmonized technical specification EN 13986:2004+A1:2015
- Essential characteristics and performances**

Thickness (mm)		12	15	18	21	24	25	27	30
Number of plies		5	5	7	7	9	9	9	11
RESISTANCE (N / mm ²)									
Tension f_t	//	15,2	15,7	17,7	15,1	11,5	13,2	14,8	11,2
	└┘	10,3	12	10	12,6	12	13,9	12,9	12,4
Compression f_c	//	26	26,9	30,4	26	19,8	22,6	25,4	19,2
	└┘	17,7	20,6	17,1	21,5	20,6	23,8	22,1	21,2
Bending f_m	//	23,2	24,4	23	20,4	17	14,9	18,6	15,5
	└┘	10,2	13,7	12,1	15,1	12,5	15,5	14,8	12,7
Planar shear f_r	//	2,1	0,5	0,5	0,5	2,1	0,5	0,5	2,1
	└┘	0,5	0,5	2,1	0,5	0,5	0,5	0,5	0,5
Panel shear f_v	//	5,9	5,9	5,9	5,9	5,9	5,9	5,9	5,9
	└┘	5,9	5,9	5,9	5,9	5,9	5,9	5,9	5,9
MODULUS OF ELASTICITY (N / mm ²)									
Tension E_t	//	5619	7052	7968	6802	6097	5936	6668	5908
	└┘	4627	5398	4482	5648	6353	6250	5782	6542
Compression E_c	//	5619	7052	7968	6802	6097	5936	6668	5908
	└┘	4627	5398	4482	5648	6353	6514	5782	6542
Bending E_m	//	7596	9152	9220	8188	7983	6444	7695	7500
	└┘	2078	3298	3230	4262	4467	4815	4755	4950
Planar shear G_r	//	95	95	95	95	95	95	95	95
	└┘	95	95	95	95	95	95	95	95
Panel shear G_v	//	548	548	548	548	548	548	548	548
	└┘	548	548	548	548	548	548	548	548

REACTION TO FIRE*	End use condition	Minimum thickness	Class excluding floorings	Class floorings
	Without an air gap behind the panel	9 mm	D-s2,d0	Dfl-s1
	With a closed or an open air gap not more than 22 mm behind the woodbased panel	9 mm	D-s2,d2	-
	With a closed air gap behind the wood-based panel	15 mm	D-s2,d1	Dfl-s1
	With an open air gap behind the wood-based panel	18 mm	D-s2,d0	Dfl-s1
	Any	3 mm	E	Efl
THERMAL CONDUCTIVITY (W/m.K)		$\lambda = 0,13$		

* In reference to table 8 of EN 13986 - 2004+A1:2015

MEAN STIFFNESS IN BENDING UNDER CONCENTRATED LOAD R_{mean} (N / MM) - IAW EN 12871

T (mm)	Span l (mm)								
	400	500	600	700Z	800	900	1000	1100	1200
12	378	310	242	173	104	60	55	54	45
15	543	455	372	268	162	98	74	78	69
18	814	691	561	429	288	210	184	171	129
21	1124	993	831	600	406	328	286	231	179
24	1285	1135	950	686	464	375	327	264	204
27	1756	1464	1132	829	621	505	420	348	270
30	1951	1627	1258	921	690	561	467	387	300

ULTIMATE CHARACTERISTIC STRENGTH UNDER CONCENTRATED LOAD - $F_{max,k}$ (kN) - IAW EN 12871

T (mm)	Span l (mm)								
	400	500	600	700	800	900	1000	1100	1200
12	2,29	2,18	2,07	1,96	1,84	1,79	1,74	1,69	1,64
15	3,13	3,02	2,88	2,66	2,45	2,39	2,34	2,28	2,21
18	4,35	4,13	3,91	3,69	3,32	3,26	3,19	3,13	3,01
21	5,36	5,15	4,94	4,46	3,97	3,90	3,84	3,69	3,52
24	6,12	5,88	5,64	5,09	4,54	4,46	4,39	4,22	4,03
27	7,58	7,07	6,56	6,05	5,54	5,36	5,18	5,00	4,82
30	8,42	7,86	7,29	6,72	6,16	5,96	5,76	5,56	5,36

SERVICEABILITY CHARACTERISTIC STRENGTH UNDER CONCENTRATED LOAD - $F_{ser,k}$ (kN) - IAW EN 12871

T (mm)	Span l (mm)								
	400	500	600	700	800	900	1000	1100	1200
12	1,61	1,58	1,55	1,53	1,5	1,45	1,40	1,35	1,31
15	2,15	2,12	2,09	2,03	1,97	1,93	1,88	1,85	1,82
18	3,01	2,95	2,89	2,83	2,66	2,63	2,61	2,58	2,52
21	3,80	3,74	3,68	3,42	3,15	3,12	3,09	3,03	2,94
24	4,34	4,28	4,21	3,91	3,60	3,57	3,53	3,46	3,36
27	5,5	5,22	4,93	4,64	4,36	4,27	4,19	4,10	4,01
30	6,11	5,80	5,48	5,16	4,84	4,74	4,66	4,56	4,46

RACKING RESISTANCE (WALL SHEATHING ON STUDS)	IAW EN 12871 : To obtain the values by mean of calculation, use EN 1195-1-1 with a density of 540 (kg/m ³)	
IMPACT RESISTANCE	In conformity with the requirements of EN 12871 in impact resistance	
WATER VAPOUR PERMEABILITY	μ Wet cup	μ Dry cup
	44	187
RELEASE OF FORMALDEHYDE	$\leq 0,062$ mg/m ³ , 1/2 E1 IAW EN 717-1	
CONTENT OF PENTACHLOROPHENOL	PCP < 5 ppm	
AIRBORNE SOUND ABSORPTION	NPD The sound transmission loss R of a single wood-based panel, measured in dB, is related the mean surface mass mA en kg/m ² according to the following equation (which is only valid for the frequency range of 1 kHz to 3 kHz and at a surface mass > 5 kg/m ²): $R = 13 \times \lg (mA) + 14$	

SOUND ABSORPTION (COEFFICIENT)	Frequency range 250 Hz to 500 Hz	Frequency range 1000 Hz to 2000 Hz
	0,10	0,30
EMBEDMENT STRENGTH	NPD To obtain the values by mean of calculation, use EN 1195-1-1 with a density of 540 kg/m ³	
AIR PERMEABILITY (FLOW)	0,0 m ³ /(h.m ²)	
BONDING	Class 3 (EN 636-3) according to EN 314-2	

MODIFICATION FACTOR k_{mod}	Service class	Duration of load				
		Permanent	Long	Medium	Short	Instantaneous
	1 and 2	0,60	0,70	0,80	0,90	1,10
	3	0,50	0,55	0,65	0,70	0,90
DEFORMATION FACTOR k_{def}	Service class					
	1	2	3			
	0,80	1,00	2,50			
BIOLOGICAL DURABILITY - USE CLASS	3					

10. **Performance of the product:**
 The performance of the product identified in points 1 and 2 is in conformity with the declared performance of point 7.
 This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4.

Signed on behalf of the manufacturer by :

Antoine THEBAULT, President
 Issued in Magné - 18/03/24