

# TEBOPIN CLEAR

FT TEBOPIN CLEAR · REF 26-V1-GBINC24 · Cancels and supersedes any previous versions



All applications where the natural aesthetic of the wood is very important and where the reverse side may remain occasionally or partly visible.

Joinery works, shelving, DIY, internal fittings, timber framed constructions.



## DESCRIPTION

**Base board:** Maritime Pine faced plywood with Maritime Pine and/or Scots Pine core layers

**Faces** (IAW EN 635-3): I++ / II



**Finishing:** sanded 2 sides

**Average density** (IAW EN 323): 580 kg/m<sup>3</sup> (+/- 10%)

**Bonding** (IAW EN 314-2): class 3

**Service** (IAW EN 636): class 3 exterior conditions

**Formaldehyde release classification:** E1 IAW EN 717-1 · REACH 2023/1464 compliant

**Content of Pentachlorophenol** (IAW EN 13986): PCP ≈ 0 ppm

## SIZES, NUMBER OF PLYS & PACKAGING

Thicknesses (mm)	Number of plies	Sizes (mm)	Packing
10	(5)	2500 x 1250 2400 x 1220	45
12	(5)		37
15	(5)		30
18	(7)		25
21	(7)		22
25	(9)		18
27	(9)		15
30	(11)		15
35	(13)		13
40	(15)		11
45	(17)	10	

Other sizes & thicknesses: on request

## OPTIONS

Preservative treatments, fungicide & Insecticide, antitermite: optional on request

Cutting & TG processing: optional on request

## STORAGE

Flat, on intermediate bearers, in an enclosed dry and ventilated building, clear of the ground. As far as storage on site is concerned, provision should be made to cover the panels with an opaque waterproof sheeting with the underside of the stacks clear of the ground.

## FURTHER PROCESSING & INSTALLATION

Compliance with standard practice, with regulations and with health and safety rules should be maintained at all times.

Cutting and machining in the workshop possible except laser technology.

## PRODUCTION SITES

Production on Thébault's sites in France



Groupe THEBAULT  
47, rue des Fontenelles - 79 460 MAGNE - France  
Tél : +33 (0)5 49 35 70 20 - Fax : +33 (0)5 49 35 21 10  
info@groupe-thebault.com

[www.groupe-thebault.com](http://www.groupe-thebault.com)



## TECHNICAL PROPERTIES

### Characteristic values (MPa) IAW EN 789 - 1058 for structural calculations IAW Eurocodes

		10	12	15	18	21	25	27	30	35	40
Modulus of elasticity ( $E_m$ )	//	8723	7596	9152	9220	8188	6444	7695	7500	7093	6824
	└┬	3727	2078	3298	3230	4262	4815	4755	4950	5357	5626
Bending strength ( $f_m$ )	//	20,3	23,2	24,4	23,0	20,4	14,9	18,6	15,5	15,9	16,9
	└┬	17,8	14,8	13,7	12,1	15,1	15,5	14,8	12,7	15,2	15,1
Others characteristic values	Available on DOP Strength in: Tension ( $f_t$ ), Compression ( $f_c$ ), Panel shear ( $f_v$ ) and Planar shear ( $f$ ) Modulus of elasticity in: Tension ( $E_t$ ), Compression ( $E_c$ ), Panel shear ( $G_v$ ) and planar shear ( $G$ )										

### Uses

Use in structural applications (IAW EN 13986, EN 636-3, EN 636-2, EN 636-1)	Suitable for use as structural element in exterior conditions (service class 3), humid conditions (service class 2) and interior conditions (service class 1)
--	---

### Bending radius (mm)

Thickness	10	12	15	18
//	2500	3000	3750	4750
└┬	2000	2400	3000	3800

### Nail and screw holding (t = 15 mm)

Nail	Face and edge: 300 N	
Screw	Face	Edge
	1450 N	1150 N

### Sound absorption coefficient

IAW EN 13986 Table N°10	Frequency range	
	250 Hz to 500 Hz	1000 Hz to 2000 Hz
	0,10	0,30

### Thermal conductivity

IAW EN 13986	$\lambda = 0,13$
--------------	------------------

### Characteristic density

IAW EN 789	540 kg/m <sup>3</sup>
------------	-----------------------

### Vapour permeability

IAW EN 13986 Table 9	Wet cup	Dry cup
	44 $\mu$	187 $\mu$

### Reaction to fire

End use condition In reference to table 8 of EN 13986 - 2004+A1:2015	Minimum thickness	Class excluding floorings	Class floorings
Without an air gap behind the panel	9 mm	D-s2,d0	D <sub>fl</sub> -s1
With a closed or an open air gap not more than 22 mm behind the woodbased panel	9 mm	D-s2,d2	-
With a closed air gap behind the wood-based panel	15 mm	D-s2,d1	D <sub>fl</sub> -s1
With an open air gap behind the wood-based panel	18 mm	D-s2,d0	D <sub>fl</sub> -s1
Any	3 mm	E	E <sub>fl</sub>

### Airbone sound absorption

IAW EN 13986 Paragraph 5.10	The sound transmission loss R of a single wood-based panel, measured in dB, is related the mean surface mass $m_A$ en kg/m <sup>2</sup> according to the following equation (which is only valid for the frequency range of 1 kHz to 3 kHz and at a surface mass > 5 kg/m <sup>2</sup> ): $R = 13 \times \lg(m_A) + 14$
--------------------------------	---

## TECHNICAL SUITABILITY & CERTIFICATION

<b>CE Structure attestation of conformity 2+</b>	0380 - DOP* - CPR - EN 13986 : 2004 + A1 : 2015 - EN 636-3 S E1 * DOP : Declaration of Performance available on <a href="http://www.groupe-thebault.com">www.groupe-thebault.com</a>
--	---

CE Marking	Service	Wood resource		Recyclability
		PEFC	EUDR	
CE S (Structural)	Exterior			