FT TEBOPROFIL · REF 25-V1-GB · Cancels and supersedes



Wall cladding, gables, roof ends and attics, finishing of eaves, garage doors, wooden structures.






Groupe THEBAULT 47, rue des Fontenelles - 79 460 MAGNE - France Tél : +33 (0)5 49 35 70 20 info@groupe-thebault.com

www.groupe-thebault.com

DESCRIPTION Base board: throughout Okoume plywood produced from severely selected veneers

Faces (IAW EN 635-2): || / ||| Further processing of the face side: U Groove Finishing: sanded 2 sides Further processing of the edges: Shiplapped

Further processing profile (10 mm)



Average density (IAW EN 323): 500 kg/m3 (+/- 10%) Bonding (IAW EN 314-2): class 3 Service (IAW EN 636): class 3 exterior conditions

Formaldehyde release classification (IAW EN 717-1): E0.5 (≤ 0,062 mg/m³) Content of Pentachlorophenol (IAW EN 13986): PCP ≈ 0 ppm

SIZES, NUMBER OF PLIES & PACKAGING

Thicknesses (mm)	Number of plies	Sizes (mm)	Packing
10	(5)		45
15	(7)	2500 x 1205	30

Other sizes & thicknesses: on request

OPTIONS

Preservative treatments, fungicide & Insecticide, antitermite: optional on request Cutting & TG processing: optional on request

STORAGE

Flat, on intermediate bearers, in an enclosed dry and ventilated building, clear of the ground. As far as storage on site is concerned, provision should be made to cover the panels with an opaque waterproof sheeting with the underside of the stacks clear of the ground.

FURTHER PROCESSING & INSTALLATION

Compliance with standard practice, with regulations and with health and safety rules should be maintained at all times.

Cutting and machining in the workshop possible except laser technology

PRODUCTION SITES

Production on Thébault's sites in France





TEBOPROFIL TECHNICAL PROPERTIES



Applications

 \triangleleft

 \square

Humid conditions	Conditions corresponding to service class 2 of ENV 1995-1-1 which is characterised by a moisture content in the material corresponding to a temperature of 20 $^\circ$ C and a relative humidity of the surrounding air only exceeding 85 $\%$ for a few weeks per year
External Conditions	Conditions corresponding to service class 3 of ENV 1995-1-1 which is characterised by climatic conditions leading to higher moisture contents than in service class 2

Bending radius (mm) Nail and screw holding (t = 15 mm) Thicknesses 10 15 Face and edge: 300 N Nail // NPD NPD Face Edge _|_ Screw 1450 N 1150 N Sound absorption coefficient **Reaction to fire** Frequency range Class End use condition Minimum Class In reference to table 8 of EN 13986 - 2004+A1:2015 IAW EN 13986 excluding 250 Hz to 500 Hz 1000 Hz to 2000 Hz thickness floorings Table N°10 floorings 0,10 0,30 Without an air gap behind the panel 9 mm D-s2,d0 D_{fl}-s1 Thermal conductivity With a closed or an open air gap IAW EN 13986 $\lambda = 0,13$ not more than 22 mm behind 9 mm D-s2.d2 _ the woodbased panel **Characteristic density** With a closed air gap behind 15 mm D-s2,d1 D_{fl}-s1 IAW EN 789 430 kg/m³ the wood-based panel With an open air gap behind Vapour permeability D-s2,d0 18 mm D_{fl}-s1 the wood-based panel Wet cup Dry cup IAW EN 13986 Table 9 Е E_{fl} Any 3 mm 70 µ 200 µ

Airbone sound absorption

IAW EN 13986 Paragraph 5.10 The sound transmission loss R of a single wood-based panel, measured in dB, is related the mean surface mass m, en kg/m² according to the following equation (which is only valid for the frequency range of 1 kHz to 3 kHz and at a surface mass > 5 kg/m²): $R = 13 \times Ig (m_s) + 14$

TECHNICAL SUITABILITY & CERTIFICATION

CE Structure attestation of conformity 1

0380 - DOP* - CPR - EN 13986 : 2004 + A1 : 2015 - EN 636-3 E1 * DOP : Declaration of Performance available on www.groupe-thebault.com

Quality marks (country)	CE Marking	Information on the emission level of volatile substances within the indoor air, showing a risk of toxicity in case of inhalation, based on a scale going from A+ (very low emissions)	
NF Extérieur CTB-X (F)	CE (Non Structural)		
CONTREPLAQUÉS WWW.fcba.fr	CE	Emissions). Scenarios flooring/ceiling	